



®HEBI HIGER CHEMICAL TECHNOLOGY CO., LTD.

ADD: JIJASHAN INDUSTRIAL PARK, HEBI CITY, HENAN PROVINCE, CHINA.

TEL: +86-392-3296888

WEB: www.chemresin.com

FAX: +86-392-2566666

EMAIL: higer@chemresin.com

Strong Base Anion Resin 201X7

This anion exchange resin is styrene and divinyl benzene copolymer cross linked with quaternary amine[-N(CH₃)₃OH]. It is mainly used for pure water and ultrapure water preparation, water desalination, wastewater treatment, extraction of biochemical products.

Characteristics

Item	201X7
Appearance	Light yellow to gold yellow beads
Matrix	Styrene/DVB Gel
Ionic Form	Cl ⁻
Mass total exchange capacity mmol/g(dry)	≥ 3.50
Volume total exchange capacity mmol/ml	≥ 1.35
Moisture content %	42.00 - 48.00
Bulk density g/ml	0.67 - 0.73
Specific density g/ml	1.07 - 1.10
Particle size %	(0.315-1.25mm) ≥ 95.0 (<0.315mm) ≤ 1.0
Whole Beads Rate %	≥ 95.0
Uniformity coefficient	≤ 1.6

Packing:

- Woven bags lined with plastic sheets 25L/bag
- PE valve bags 25L/bag
- Supersacks 1000L/bag

Storage:

The recommended storage temperature is 5-40°C.
Prohibited exposure, dehydration, contamination.